



ICI Devoe Coatings is a member of the ICI Paints World Group

CATHA-COAT® 315HA

Organic Zinc Rich Epoxy Primer

Cat. # 315HAXXX
(Special Order)

PRODUCT DESCRIPTION

Generic: Organic Zinc Rich Epoxy

General Description: A high performance, two component, organic zinc-rich primer with proven cathodic protection of steel structures.

This unique formula features a pre-mixed zinc base which, when converted, can be applied over commercial abrasive-blasted steel (SP6, Sa2). Most ICI Devoe Coatings High Performance Finishes can be applied as soon as solvents evaporate from the film without topcoat bubbling normally experienced over inorganic zinc-rich primers.

Typical Uses: Ideal for cathodic protection of steel structures, tanks, equipment, piping and other steel surfaces exposed in mild to severe industrial environments. Also ideal for touch-up and maintenance work because of its easy application, wide compatibility and fast dry-to-recoat.

Special Qualifications: Meets Class B slip and creep for faying surfaces.

FEATURES

Advantages:

- Exceptional corrosion resistance
- Provides cathodic protection
- Easy to mix
- Zinc premixed in base component
- Fast dry to handle and recoat
- Formulated to resist topcoat bubbling
- Applies easily by brush, roll or spray
- Accepts a wide variety of topcoats for severe exposures
- Formulated without lead, chromate, or mercury components

Limitations of Use: Do not topcoat with alkyd or alkyd-urethane coatings. Not suitable for solvent or chemical immersion.

SPECIFICATION DATA

Color: Green (315HA225)

Finish: Flat

Reduction Solvent: T-10 Thinner

Clean-up Solvent: T-10 Thinner

Weight/Gallon: 24.8 lbs./gal. (2.97 kg/L)

VOC: (EPA 24) 2.46 lbs./gal. (295 g/L)

Solids By Volume: (ASTM D 2697-7days): 74%

Theoretical Coverage at 1.0 Mil Dry: 1187 sq. ft./gal. (29.6 m²/L)

Recommended Film Thickness: 3.0-4.0 mils (75-100 microns) dry – 4-5.4 mils (100-135 microns) wet

Systems: Please consult the appropriate system guide, the particular job specification or your ICI Devoe Coatings' Industrial Coatings Specialist for proper systems using this product. Systems must be selected considering the particular environment involved.

Service Temperature Limits: 400°F (193°C) dry, intermittent

Minimum Dry Time (ASTM D 1640): At 3 mils (75 microns) DFT

Substrate Temperature	40°F (4°C)	77°F (25°C)	90°F (32°C)
To recoat	5 hours	2 hours	1 hours
Dry hard	20 hours	5 hours	2 hours

Ventilation, film thickness, humidity, thinning and other factors can influence the rate of dry.

Warning: The above table provides general guidelines only. Always consult your ICI Devoe Coatings Specialist for appropriate recoat windows since the maximum aged recoat time of this product may be significantly shortened or lengthened by a variety of conditions, including, but not limited to humidity, surface temperature, and the use of additives or thinners. The use of accelerators or force curing may shorten the aged recoat of individual coatings. The above recoat windows may not apply if recoating with a product other than those listed above. If the maximum aged recoat window is exceeded, please consult your ICI Industrial Coatings Specialist for appropriate recommendations to enhance adhesion. Failure to observe these precautions may result in intercoat delamination.

Shelf Life: Over 24 months at 77°F (25°C) – unopened

Hardness (ASTM D 3363, 7 day cure @ 77°F (25°C): 6H

Mix Ratio By Volume: 4.6 (base): 0.4 (converter) – see mixing instructions.

Induction: 15 minutes minimum below 60°F (16°C) – see mixing instructions.

Pot Life: 8 hours @ 77°F (25°C) & 50% R.H.

PERFORMANCE DATA

Salt Spray Resistance (ASTM B 117) – Excellent

Direct Impact Resistance (ASTM D 2794) – Good

Humidity Resistance (ASTM D 2247) – Excellent

Water Immersion (ASTM D 1308) – Excellent

GENERAL SURFACE PREPARATION

All surfaces must be sound, dry, clean and free of oil, grease, dirt, mildew, form release agents, curing compounds, loose and flaking paint and other foreign substances, and be structurally sound. Round off welds and sharp edges and remove weld splatter.

New Surfaces: Steel – Abrasive blast to minimum SSPC-SP6, (SSI-Sa2). A cleaner surface (i.e. SSPC-SP10, SSI-Sa2½ near-white) will enhance primer and system performance. The blast profile should be jagged rather than "peened" and between 1½

to 2½ mils (38-62 microns). After blasting, vacuum or blow off all abrasive dust and ensure surface remains clean before painting.

Previously Painted Surfaces: Remove old paint to bare metal. Prepare surface and prime as for new steel. Achieve a minimum of SSPC-SP6 (SSI-Sa2) on rough or pitted steel.

DIRECTIONS FOR USE

Tinting: Do not tint.

Thinning: Thinning is not normally required or desirable. However, at lower temperatures, small amounts (10% or less) of Devco T-10 Thinner can be added to the mixed components depending on local VOC and air quality regulations.

Mixing: CATHA-COAT 315HA Primer is supplied in a 3 gallon kit which contains the proper ratio of ingredients. The entire contents of each container must be mixed together. The zinc metal is ready-mixed in the base portion. Stir thoroughly with a slow speed mixer while slowly adding the converter. Continue to mix at slow speeds to a homogeneous condition. At temperatures of 60°F (16°C) or above, allow a 15 minute induction time before using. Add about 10 minutes for each 10°F (6°C) lower temperature. The pot life, 8 hours at 77°F (25°C), will be longer at lower temperatures and shorter at higher temperatures.

Application: Spray, roller or brush. Use brush and roller primarily for touch-up and repair. Spray is preferred for uniform film build. Use agitated spray pots. For air spray, use .070" or larger tip, 15 psi fluid pressure, fluid hose 1/2" I.D. and maximum 50 ft. length. For airless spray use a sprayer capable of

3,000 psi (207 bars) and able to support a .025" diameter tip, fluid hose 3/8" I.D. and maximum 50 ft. length. Pressure pots or pumps should be at same level or above spray guns. Keep fluid pressures to minimum. Rough or heavily pitted steel requires higher (or increased) dry film thickness for optimum protection. Care should be taken to ensure that proper film thicknesses are applied. Brushing and rolling may require multiple coats to achieve correct film thickness and/or hiding.

Spreading Rate: Apply at 297-396 sq.ft. per gallon (7.5-10 m²/L) depending on surface texture and porosity. Make allowances for any losses due to overspray or surface irregularities.

Topcoats: CATHA-COAT 315HA can be readily recoated by itself for easy touch-up. May be topcoated with DEVCO® 224HS or BAR-RUST™ Epoxy Coatings. No tie coat is required before applying finish coat. Do not topcoat with alkyd or alkyd-urethane coatings.

Dry Time: At 77°F (25°C) & 50% R.H., dries to recoat in 2 hours; hard 5-6 hours.

Clean-up: Use T-10 Thinner.

PRECAUTIONS

DANGER! FLAMMABLE LIQUID AND VAPOR. CORROSIVE. CAUSES EYE AND SKIN BURNS. HARMFUL OR FATAL IF SWALLOWED. ASPIRATION HAZARD-CAN ENTER LUNGS AND CAUSE DAMAGE. HARMFUL IF INHALED. MAY CAUSE CENTRAL NERVOUS SYSTEM EFFECTS, INCLUDING DIZZINESS, HEADACHE OR NAUSEA. CAUSES RESPIRATORY TRACT IRRITATION. MAY CAUSE ALLERGIC SKIN AND RESPIRATORY REACTION. MAY BE HARMFUL IF ABSORBED THROUGH SKIN. OVEREXPOSURE MAY CAUSE BLOOD, LIVER, KIDNEY DAMAGE. CONTAINS CRYSTALLINE SILICA WHICH CAN CAUSE LUNG CANCER AND OTHER LUNG DAMAGE IF INHALED. USE ONLY WITH ADEQUATE VENTILATION. KEEP OUT OF THE REACH OF CHILDREN. NOTICE: Products in this series contain solvents. Reports have associated repeated and prolonged occupational overexposure to solvents with permanent brain and nervous system damage. Intentional misuse by deliberately concentrating and inhaling the contents may be harmful or fatal. For emergency information call (800) 545-2643. Keep away from heat, sparks and flame. **Do not** smoke. Vapors may ignite. Extinguish all flames, burners, stoves, heaters and pilot lights and disconnect all electrical motors and appliances before use and until all vapors are gone. If sanding is done, wear a dust mask to avoid breathing of sanding dust. Do not breathe vapors or spray mist. If you experience eye watering, headaches, or dizziness, leave the area. If properly used, a respirator may offer additional protection. Obtain professional advice before using. Close container after each use. **FIRST AID:** In case of skin contact, wash off **quickly** with plenty of soap and water, remove contaminated clothing. For eye contact flush immediately with large amounts of water, for at least 15 minutes. **Obtain emergency medical treatment.** If swallowed, **obtain medical treatment immediately.** If inhalation causes physical discomfort, remove to fresh air. If discomfort persists or any breathing difficulty occurs, **get medical help.** **Note: These warnings encompass the product series. Prior to use, read and follow product-specific MSDS and label information.**

DS240-1099

SHIPPING

Freight Classification: Paint, 3, PG III, UN1263 (Flammable Liquid)
Flash Point: 80°F (27°C)
Packaging: 3 gallon kit (11.35L)
 2.76 gallon base
 0.24 gallon converter
 Will be packaged in a five gallon pail

Shipping Weight: 3 gallon kit - 80 lbs. (36 kg)

315HAXXX (10/01)
 Ad Stock #67012D



Cleveland,
 Ohio, U.S.A.
 800-654-2616
www.devcocoatings.com

ICI Devco Coatings is a member of the ICI Paints World Group

LIMITATION OF LIABILITY: To the best of our knowledge, the technical data contained herein are true and accurate at the date of issuance but are subject to change without prior notice. We guarantee our product to conform to the specifications contained herein. WE MAKE NO OTHER WARRANTY OR GUARANTEE OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND FITNESS FOR PARTICULAR PURPOSE. Liability, if any, is limited to replacement of the product or refund of the purchase price. LABOR OR COST OF LABOR AND OTHER CONSEQUENTIAL DAMAGES ARE HEREBY EXCLUDED.